

COLD GAL SPRAY PAINT

TECHNICAL DATA SHEET

Product Name: CSS Cold Gal

Reference No: CAM001702

Issued: 2016-04-28

Version: 1.0

Page 1 of 7

Product Name:	CSS COLD GAL	Telephone:	+61 3 9357 4228
Product Code:	CSSCG	Fax:	+61 3 9357 4229
Synonyms:	CSS Cold Gal	Website:	www.constructionsupply.com.au
Recommended Use:	Paint		
Supplier:	Construction Supply Specialists Pty Ltd		
ABN:	45 161 688 571		
Street Address:	6 Broadfield Road Broadmeadows VIC, 3047 Australia		

**EMERGENCY PHONE NUMBER: 03 9357-4228
(Mon-Fri; 8am-4:30pm; AEST)**

Zinc Spray is a fast-drying protection from corrosion with excellent long-term effect for metals. In dry film, Zinc Spray contains more than 90% zinc and zinc compounds. Adheres to almost all metals, has a smooth and penetrating film. Can be used in spot-welding and is heat-resistant up to 500°C. Can be lacquered over.

Zinc Spray can be used

- In repairing damaged zinc layers
- In coating drilling, cutting and welding points
- As a conducting intermediate layer in spot-welding
- As a primary coat for installations at risk from water and weather effects
- With all bodywork
- Everywhere where metal must be protected from corrosion

Zinc Spray can be applied in all sectors of industry and trade as well as in body manufacturing, particularly in areas where metals are exposed to corrosion.

- DIN 53167 salt spray test in combination with DIN 50021: 400 hours/80 my < 0,5 mm
- DIN 53151 cross-cut test: Gt 0-1

Use:

Ideal temperature 16°C – 25°C. Degrease metals and grind them smoothly. Shake the spray vigorously for about three minutes after the clearly audible striking of the metal ball. Apply the spray crosswise from a distance of approx. 25-30cm. The surface is dry after 5-7 minutes, fast to handling after 20-30 minutes and completely dry after approx. 24 hours.

Content of aerosol can: 400 ml

Our information sheets and other publications are intended to provide advice based on the best knowledge at our disposal. However, contents are not legally binding with regards to processing and application as these do not fall within our field influence. The right is reserved to make modifications in the interests of improvement or further development of the product.

